



# NEWS 94

## HARDDOT ARGON SCANNER FILM

### Description

NEWS 94 incorporates the latest HardDot emulsion technology.

For trouble free use, this film has antistatic protection and excellent surface resistance properties.

NEWS 94 has extremely high resolution, and is fully linearized for complete, but simple calibration.

### Sensitivity

NEWS 94 HardDot 488mm (Argon Ion)

### Safelight

Standard Red, or Yellow/Orange Light  
(EncapSulite A5-ND 0.3 or equivalent)

### Processing

*Developer\**:

#1 Network HardDot Developer  
Mixed 1 part with 2 parts water

*Temperature:* 95°F / 35°C

*Development Time:* 30 Seconds

### Replenishment Rates

Developer: 45ml per square foot (1.53 oz.)  
Fixer: 35ml per square foot (1.2 oz.)  
#1 Network Universal Fixer Concentrate,  
3100 Fixer recommended with hardener.

### Procedure For Processing

- 1) Cut a 3 or 4 inch strip from film protruding from supply cassette.
- 2) With processor at recommended settings, develop the excessively exposed strip.
- 3) When properly and adequately developed, the strip D/Max should be 5.50 to 6.20.

**With full development,  
the emulsion sensitivity is maximized.**

- 4) With a minimum of 5.50 D/Max, NEWS 94 is ready for exposure calibration in the imagesetter.

### Exposure Calibration

NEWS 94 may be calibrated to accurately obtain a 50% dot, or 5.00 to 5.20 D/Max in the 100% solid square.

**IMPORTANT:** HardDot films must be processed in a **recommended "HD"** developer diluted 1-part concentrate to 2-parts water. It is also important to replenish at the recommended rates. Additional "anti-oxidation" replenishment may be required. Total replenishment should equal **at least** 1/2 of the volume in the processor tank per week in "low load" situations.

Departure from these instructions may result in "**pepper**" or thin "**pressure lines**". Both artifacts are caused by a chemical imbalance. If pepper is encountered, you must dump the developer and increase replenishment.

### Note:

When you install new films or processor chemicals, it is a good ideal to run a few "**Dr. Clean**" cleaner sheets.

"**Dr. Clean**" cleaner sheets will virtually eliminate any potential for pinholes and ensure that every #1 Network film will look it's very best!

\*For optimum results, process in 4th generation chemistry diluted with 2 parts water.

#1 Network 2100 HD\* Developer  
#1 Network Rapid HD\* Developer  
Kodak RA 2000  
Fuji Forte HQ

\*HD refers to HardDot when mixed 1:2.

These developers are also rapid access developer, when mixed 1:3 or 1:4.